

CND PLEXIGEL™ COLOR BUILDER

WHAT IT IS

A brush-on gel enhancement that provides strength, architecture, and moderate/long length to the natural nail in a variety of natural skin tone shades.

WHAT IT DOES

- Creates strong, lightweight, medium to long enhancements on nails requiring more shape or length transformation.
- Provides versatile service options; can be used over a tip or a sculpting form for customizable length.
- Allows for buildable coverage from semi-sheer to semi-opaque.

WHY YOU NEED IT

- Comes in 5 shades suitable for all skin tones —



Porcelain Oat Milk Soft Blush Spiced Taffy Milky Mauve.

- Saves on service time by having enhancement and color in one.
- Thicker viscosity allows for control and buildability.
- Self-Smoothing formula for less filing.
- Can be rebalanced or removed.

DIRECTIONS FOR USE

- Perform P.R.E.P. and apply a tip or form.
- Apply a layer of **CND PLEXIGEL™** Bonder to the natural nail. Cure for 10 seconds in the **CND™** LED Lamp using preset button 1.
- **PRO TIP:** Applying a thin layer of **CND PLEXIGEL™** Shaper or Builder to the natural nail and curing for one minute using preset button 2B is recommended for color rebalancing.
- Sculpt nails to the preferred length and shape using **CND PLEXIGEL™** Color Builder. Cure for one minute using preset button 2B.
- Repeat to build architecture and color. Cure for one minute using preset button 2B.
- Clean the nail with Isopropyl Alcohol. Shape and refine using **CND™** files and buffers.
- Apply **CND PLEXIGEL™** Protector Topcoat and cure using preset button 3.

Visit cnd.com for complete Step-by-Step instructions.



AVAILABLE SIZES

- Professional: 15 mL (.5 fl oz)

INGREDIENT LISTING

Bis-HEMA Poly(1,4-Butanediol)-22/IPDI Copolymer, Tetrahydrofurfuryl Methacrylate, Cellulose Acetate Butyrate, Hydroxypropyl Methacrylate, Isopropylidenediphenyl Bisoxhydroxypropyl Methacrylate/TMDI Copolymer, Bis-HEMA Poly(Caprolactone Neopentyl Glycol)/IPDI Copolymer, Triethylene Glycol Dimethacrylate, Isopropylidenediphenyl PEG-2 Dimethacrylate, Silica, Isopropylidenediphenyl Bisoxhydroxypropyl Methacrylate, Bis-HEMA Poly(Caprolactone/Pentaerythritol)/IPDI Copolymer Succinate, Trimethylbenzoyl Diphenylphosphine Oxide, Bis-Trimethylbenzoyl Phenylphosphine Oxide, Drometizole, PPG-5 Methacrylate, Silica Dimethicone Silylate, BHT, p-Hydroxyanisole

CND™